

Product / Application
Internal Walls
Float Base Coat

Mix Design by Volume	
Plasterers Cement	Sand
1	5

Qty per 100m ² of Render		
Plasterers Cement (20kg)	Extra Hydrated Lime	Sand
14	0	1.6m ³

External Walls	
Sand Finish (one coat)	
2 Coat Finish	• Base Coat (10mm thick)
	• Top Coat (3mm thick)

1	3
1	5
1	2

20	0	1.6m ³
14	0	1.6m ³
5	0	0.5m ³

- i** **NOTE:**
1. Clean, sharp, well-graded sand, free from loam, clay and impurities should be used.
The presence of foreign matter will weaken mortar and affect its setting time.
 2. Plasterers Cement contains hydrated lime and an air-entraining agent for better workability. The use of additional additives is not required or recommended.
 3. To reduce colour variations to sand-finished renders, avoid multiple sand deliveries.

