



TYPE **GP**
GENERAL PURPOSE CEMENT

Typical Analysis

	Typical BGC Value	Typical BGC Range	AS 3972	Units
Mortar Compressive Strengths				
3 day	34	27 – 42	-	(MPa)
7 day	45	39 – 52	<i>Min. 35</i>	(MPa)
28 day	55	50 – 60	<i>Min. 45</i>	(MPa)
Vicat Setting Time				
Normal Consistency	29.0	28.6 – 29.3	-	(%)
Initial Set	105	90 – 120	<i>Min. 45</i>	(minutes)
Final Set	150	135 – 165	<i>Max. 360</i>	(minutes)
Residue				
+45µm	7.8	2.6 – 12.2	-	(%)
Fitness Index				
	378	364 – 393	-	(m ² /kg)
Soundness				
	1	0 – 2	<i>Max. 5</i>	(mm)
Chemical Analysis				
SO ₃	2.8	2.4 – 3.2	<i>Max. 3.5</i>	(%)
SiO ₂	19.4	19.0 – 19.8	-	(%)
Al ₂ O ₃	4.9	4.7 – 5.1	-	(%)
Fe ₂ O ₃	3.1	3.0 – 3.3	-	(%)
MgO	1.6	1.4 – 1.7	-	(%)
CaO	63.4	62.6 – 64.2	-	(%)
Loss on Ignition	3.3	2.5 – 3.9	-	(%)
Na ₂ O (equivalent)	0.6	0.4 – 0.6	-	(%)
Chloride ion	0.01	0.00 – 0.01	<i>Max 0.10</i>	(%)

Note: Typical range is at 95% confidence level, individual results may be outside of this range.

Dr Michael G Remias
Cemtech – Manager

TECHNICAL DATA SHEET

Issue Date: 29 May 2017 (For current data please check with undersigned)